

**AMENDMENTS TO THE CLAIMS**

**This listing of claims will replace all prior versions and listings of claims in the application:**

**LISTING OF CLAIMS:**

1. (currently amended): A preform including a body and a bottom portion having portion, the preform having a continuous-multi-layer structure that is continuous through the body and bottom portion, which preform is formed by compression-forming a melt-extruded molten resin mass, and continuously forming a multi-layer structure in the body portion and in the body portion thereof, the multi-layer structure having layers of an ethylene terephthalate unit-containing polyester resin as inner and outer layers and sealing at least one layer of a gas-barrier resin or a recycled polyester resin as an intermediate layer, said intermediate layer running continuously through the body and entire bottom portion,

wherein ~~the~~ a time is not shorter than 300 seconds before a calorific value of isothermal crystallization of said layer of the ethylene terephthalate unit-containing polyester resin at 210°C reaches a maximum value.

2. (previously presented): A preform according to claim 1, wherein said polyester resin contains ethylene terephthalate units at a ratio of not smaller than 95 mol%.

3. (original): A preform according to claim 1, wherein said polyester resin contains recycled polyester resins.

4. (canceled).

5. (canceled).

6. (withdrawn-currently amended): A method of producing a preform including a body and a bottom portion having portion, the preform having a continuous multi-layer structure that is continuous through the body and bottom portion, which preform is formed by compression-forming a melt-extruded molten resin mass, ~~and continuously forming a multi-layer structure in the body portion and in the body portion thereof,~~ the multi-layer structure having layers of an ethylene terephthalate unit-containing polyester resin as inner and outer layers ~~and~~ sealing at least one layer of a gas-barrier resin or a recycled polyester resin as an intermediate layer, said intermediate layer running continuously through the body and entire bottom portion,

wherein ~~the~~ a time is not shorter than 300 seconds before a calorific value of isothermal crystallization of said layer of the ethylene terephthalate unit-containing polyester resin at 210°C reaches a maximum value, which method comprises feeding a molten polyester resin having an inherent viscosity at the time of melt-extrusion of not smaller than 0.72 dL/g to a compression-forming machine and compression-forming.

7. (withdrawn): A method of producing a preform according to claim 6, wherein the temperature of melt-extruding the molten polyester resin is in a range of  $T_m + 5^{\circ}\text{C}$  to  $T_m + 40^{\circ}\text{C}$  with the melting point ( $T_m$ ) of the polyester resin as a reference.

8. (withdrawn): A method of producing a preform according to claim 6, wherein a drop of the inherent viscosity at the time of melt-extrusion from the inherent viscosity of when the polyester resin to be used is thrown into the extruder is not larger than 10%.

9. (canceled).

10. (new): A preform according to claim 1, wherein the melt-extruded molten resin mass remains in a molten state until it is subjected to the compression-forming.

11. (new): A method of producing a preform according to claim 6, wherein the melt-extruded molten resin mass remains in a molten state until it is subjected to the compression-forming.

12. (new): A preform according to claim 10, wherein said melt-extruded molten resin mass is a melt-extruded composite molten resin mass.

13. (new): A method of producing a preform according to claim 11, wherein said melt-extruded molten resin mass is a melt-extruded composite molten resin mass.